



Aerocel® ULP®

Ultra-Low Perm EPDM Pipe Insulation







Aerocel ULP

Ultra-Low Perm EPDM Pipe Insulation
Unslit Tubes & Stay-Seal® with Protape® (SSPT™)

Sub-Zero Refrigeration | DX Refrigeration VRF | Chilled Water | Cryogenic

Closed-cell elastomeric pipe insulation with ultralow permeability and built-in vapor retarder for the harshest environments and most demanding applications.

Aerocel® ULP® offers a flexible, lightweight alternative to cellular glass. Eliminates time consuming fabrication and costly product loss due to jobsite and supply chain breakage, both of which are commonly associated with cellular glass.

Select ULP whenever low operating temperatures in extreme temperatures and humidity are expected and/or when vapor drive is an overriding concern.

Available in unslit and Stay-Seal® with Protape® (SSPT™) tubes in a wide range of sizes and thicknesses to meet energy code and condensation control requirements. See back cover.

Reliable in demanding applications

Non-polar - does not induce or react with water

Lower continuous service temperature to -320°F (-196°C)

Industry's lowest permeability for a closed-cell elastomeric insulation @ .01 perm-inch!

Helps prevent corrosion under insulation (CUI)

Easy to handle and install

Flexible elastomeric foam - no breakage or fabrication when compared with cellular glass

No gloves or masks required

Available in unslit tube and SSPT™ with dual-tape closure

Suitable for interior and exterior applications**

Aeroflex insulation system solutions



Aerofix®

Light-weight, rigid pipe supports, pre-insulated with closed-cell EPDM foam rubber and encased with zero-perm EPDM polymer membrane. Includes built-in pressure sensitive Protape® closure system.



AeroFit™

Pre-fabricated fitting covers made of closed-cell EPDM rubber for fast installation on HVAC and plumbing piping.



Protape®

Zero-perm EPDM-based, self-adhering rubber tape for sealing glued insulation seams and termination points.



Aeroflex Adhesives

Specially formulated adhesives for bonding and vapor-sealing Aerocel insulation. Fast tack and LVOC formulations available.

Saves installation and operating costs

Lower thermal conductivity - reduced insulation thicknesses

No supplemental vapor retarder required for most applications*

Field-fabricated

Flexible - minimizes product waste due to breakage

Supports Indoor Air Quality

No CFCs, HFCs, HCFCs, PBDEs, formaldehyde, nitrosamine or fibers

25/50 rated (ASTM E84) and self-extinguishing (ASTM D635) thru 2-inches thick

GREENGUARD Gold Certified for low chemical emissions (VOC)

Verified Environmental Product Declarations (EPD's) and Health Product Declarations (HPD's)

Ultra-low PVC content - less than 1%

**Note: National, state & local energy codes require protection of cellular foam pipe insulation from solar radiation for exterior applications. Jackets and insulation coatings are acceptable. Adhesive tapes are not permitted.

^{*}Supplemental vapor barrier may be required in extreme low-temperature or high-humidity applications. Protective jacket required for direct-bury applications and if insulation may be subjected to mechanical damage.

Product: Closed-cell EPDM (Ethylene Propylene Diene Monomer)-based rubber elastomeric foam pipe insulation for HVAC and refrigeration piping.

Installation Instructions: www.aeroflexusa.com/wp-content/uploads/2021/06/Aeroflex_Installation-Guide_062521-1.pdf **Standard Specification:** ASTM C534 Type I Grade 1

Thermal Conductivity (K) Btu-in/hr-Ft² -oF (W/m.K)

Mean Temperature	K Value	Test Method
50°F (10°C)	0.237 (0.0342)	
75°F (24°C)	0.245 (0.0353)	
100°F (38°C)	0.252 (0.0363)	
125°F (52°C)	0.260 (0.0375)	ASTM C518/C177
150°F (66°C)	0.267 (0.0385)	
200°F (93°C)	0.282 (0.0406)	
250°F (121°C)	0.315 (0.0454)	

Physical and Operational Properties

Property	Test Value/Rating	Test Method			
Consider Temperature CONTINUOUS	-320°F to 257°F	ASTM C411 ¹			
Service Temperature, CONTINUOUS	-196°C to 125°C				
UV Resistance	Minimal Cracking or color change	ASTM G7			
Ozone Resistance	No cracking	ASTM D1171	ASTM D1171		
Water Vapor Permeability, Max	0.01 perm-inch (1.45 x 10-11 g/Pa.s.m)	ASTM E96			
Water Absorption (% by Volume), Max	0.2%	ASTM C209			
	Class V-O	UL 94			
Fig. Cafata Characteristics than 20 thickers	25/50	ASTM E84			
Fire Safety Characteristics thru 2" thickness	Pass	NFPA 90A/90B			
	Self-extinguishing	ASTM D635			
Corrosion of Stainless Steel	Non-corrosive	ASTM C692, DIN 1988			
Fungi Resistance	No Growth	ASTM C1318/G21			
Mold Resistance	No Growth	UL181 Section 13	UL181 Section 13		
Flexibility	Pass	ASTM C534	ASTM C534		
Air Erosion	Pass	UL181 Section 18	UL181 Section 18		

AEROCEL flexibility begins to decrease at -70°F and below. This does not impact the insulating properties of the material.

Additional Approvals, Certifications & Compliance

ASTM D1056, 2C1	Standard Specification for Flexible Cellular Materials-Sponge or Expanded Rubber
ANSI/ASHRAE/ICC/USGBC/IES Standard 189.1	International Green Construction Code® (igCC®)
ANSI/ASHRAE/IES Standard 90.1	Energy Standard for Buildings Except Low-Rise Residential Buildings
Buy American	Buy American, Federal Acquisition Regulation, FAR 52.225 Buy American
CA Title 24	California Building Energy Efficiency Standards
CDPH Specification 01350	California Department of Public Health (VOC Emissions)
EPA TSCA Section 6(h)	Toxic Substances Control Act Persistent, Bioaccumulative, and Toxic (PBT) Chemicals
IECC®	International Energy Conservation Code®
LEED®	U.S. Green Building Council - Leadership in Energy and Environmental Design
MEA #171-04-M	City of New York Material and Acceptance Pipe Insulation
MIL-P-15280 (Form S, Form T)	U.S. Department of Defense - Qualified Products List (06/24/2005)
REACH	European Chemicals Agency (ECHA) - Registration, Evaluation, Authorization and Restriction of Chemicals
RoHS	European Union - Restriction of Hazardous Substances

Potential LEED® Credit Contributions

Energy & Atmosphere (EA)	Prerequisite: Minimum Energy Performance		
	Credit: Optimize Energy Performance		
Materials & Resources (MR)	Credit: Building Product Disclosure and Optimization - Environmental Product Declarations (EPD), Product Specific Type III		
	Credit: Building Product Disclosure and Optimization - Material Ingredients, verified HPD		
Indoor Environmental Quality (EQ)	Credit: Low-Emitting Materials		
	Credit: Indoor Air Quality Assessment		
	Credit: Thermal Comfort		
	Credit: Acoustic Performance		
Innovation (IN)	Credit: Occupant Comfort Survey		















Aerocel® ULP® R-Values (Unslit Tube)									
Pipe Size	Pipe Size (inches)	Wall Thickness (inches)							
(inches)		1/4	3/8	1/2	3/4	1	1-1/2	2	3
1/4		1.7	3.0	4.0	6.7	10.0	17.5		
3/8		1.6	2.7	3.6	6.0	9.0	15.8	24.0	
1/2	1/4	1.5	2.5	3.4	5.5	8.3	14.4	21.9	
5/8	3/8	1.4	2.4	3.2	5.2	8.0	13.5	20.6	32.6
3/4		1.4	2.3	3.1	5.0	7.7	13.0	19.7	31.2
7/8	1/2	1.3	2.3	3.2	5.3	7.4	12.9	18.5	30.6
1-1/8	3/4	1.3	2.1	3.0	5.0	6.9	12.1	17.3	28.5
1-3/8	1	1.3	2.1	3.1	5.0	6.5	11.3	16.2	26.7
1-5/8	1-1/4		2.3	3.0	4.8	6.3	11.1	15.9	26.0
1-7/8	1-1/2		2.2	2.9	4.7	6.0	10.6	15.2	24.7
2-1/8			2.2	3.0	4.6	5.9	10.3	14.8	24.0
2-3/8	2		2.2	3.0	4.5	5.8	10.0	14.3	23.2
2-5/8			2.2	2.9	4.4	5.7	9.8	14.0	22.6
2-7/8	2-1/2		2.1	2.9	4.3	5.5	9.5	13.6	21.9
3-1/8			2.1	2.9	4.3	5.5	9.4	13.4	21.6
3-1/2	3		2.1	3.0	4.2	5.3	9.1	12.9	20.8
3-5/8			2.1	3.0	4.2	5.3	9.1	12.9	
4-1/8			2.1	2.9	4.1	5.2	8.9	12.5	20.0
4-1/2	4		2.0	2.9	4.0	5.1	8.7	12.2	19.6
5-1/8					4.0	5.1	8.5	11.9	19.0
5-1/2	5			2.8	3.9	5.0	8.4	11.7	18.6
6-1/8				2.8	3.9	4.9	8.2	11.5	
6-5/8	6			2.8	3.9	4.9	8.1	11.3	17.8

Aerocel® ULP® R-Values Stay-Seal® with Protape® (SSPT™) Tube								
Pipe Size	IPS	Wall Thickness (inches)						
(inches)	(inches)	3/8	1/2	3/4	1	1-1/2	2	
1/4				6.7	10.0			
3/8		2.7	3.6	6.0	9.0	15.8		
1/2	1/4	2.5	3.4	5.5	8.3	14.4	21.9	
5/8	3/8	2.4	3.2	5.2	8.0	13.5	20.6	
3/4		2.3	3.1	5.0	7.7	13.0	19.7	
7/8	1/2	2.3	3.2	5.3	7.4	12.9	18.5	
1-1/8	3/4	2.1	3.0	5.0	6.9	12.1	17.3	
1-3/8	1	2.1	3.1	5.0	6.5	11.3	16.2	
1-5/8	1-1/4	2.3	3.0	4.8	6.3	11.1	15.9	
1-7/8	1-1/2	2.2	2.9	4.7	6.0	10.6	15.2	
2-1/8		2.2	3.0	4.6	5.9	10.3	14.8	

